

# TOOLTECH®

## TEMPORARY FLOOR PROTECTION



**Product:** Floor protection  
**Material:** Nonwoven synthetic fleece in middle top with PE foile as liquid barrier bottom with self adhesive coating  
**Colour:** Blue/white

### Applications:

tilled floor,Parquet, laminate flooring, textile floor, Stairs, Kitchen worktops, ceramics, sanitary ware, flat work, Plants

### Features:

- Non-slip on stairs no fixation with tape, for secure construction sites.
- impermeable, protects concrete against liquids of any kind (paint, solvents)
- Extremely robust and tear-resistant
- Does not moult when wiping
- Easy installation and disposal
- It can be wiped and vacuumed
- No residues were on the ground

### Benefits:


Protects carpets, stairs, tiles against mec hanical damage and stains from spilled liquids.

Helps prevent accidents back with active antiskid

Fast and wrinkle-free design time savings

Used several times Cost savings

Environmentally friendly, Free of harmf ul substances, thermally disposable



### Technical Specification:

<b>110500</b>	<b>Temporary Floor Protection</b>		<b>Size: 40in x 45ft</b>
<b>110501</b>	<b>Temporary Floor Protection</b>		<b>Size: 40in x 90ft</b>
	<b>Value</b>	<b>Value</b>	
<b>Weight</b>	160g/m <sup>2</sup> ±10% 0.033lbs per sq.ft	EN ISO 9864	
Thickness with 0.5 kpa load (approx..50g/cm <sup>2</sup> )	1.2mm±10%	DIN 5385	
Thickness	1.6mm - 1.8mm	DIN 5385	
Maximum longitudinal tensile strength	120N/5cm ± 20%	DIN EN ISO 29073 T3	
Maximum transverse tensile strength	115N/5cm ± 20%	DIN EN ISO 29073 T3	
Maximum longitudinal extension	80% ± 20%	DIN EN ISO 29073 T3	
Maximum transverse tensile strength	90% ± 20%	DIN EN ISO 29073 T3	
Water vapour permeability of the film	25g/m <sup>2</sup> ± /24h	NP EN 1110-2001	
Abrasion resistance 1000 umdr.	1	EN ISO5470-1	
Abrasion resistance 2000 umdr.	2	EN ISO5470-1	
Abrasion resistance 3000 umdr.	2	EN ISO5470-1	



**TOOLWAY**

Head Office: 1-280 Hunter's Valley Road, Woodbridge, On, Canada L4H 3V9 | Phone: (905) 326-5450 | Fax: (905) 326-5451  
 Montreal Office: 1868 Blvd. Des Sources, Suite 115, Pointe-Claire, QC, Canada H9R 5R2 | Phone : (514) 630-5130 | Fax: (514) 695-1761  
 Atlantic Canada Office: 2 Royles Avenue, Dartmouth, NS, Canada B3B 2E5 | Phone : (902) 468-2950 | Fax: (902) 468-2929